

Retan 6000
聚氨酯面漆 6000
**PRODUCT DESCRIPTION
& INTENDED USES**

产品简介

A high gloss durable finish based on polyurethane for exposed surfaces in non-immersed areas

用于非浸水曝露区域的高光泽高性能聚氨酯面漆。

FEATURES

产品特性

- Outstanding weathering resistance and gloss retention
优秀的耐候性和保光性
- Good adhesion to epoxy primers
同环氧涂料附着力良好
- Quick drying
干燥迅速

BASIC DATA

基本数据

Color(s)

White and Other colors

颜色

白色、各色

Mixing ratio

Base/Hardener=80/10 (by wt.)

混合比率

主剂/固化剂=80/10 (重量比)

Solids content

63%

重量固体份

Film thickness

Dry : 30-60 microns/coat Wet : 65-130 microns/coat (white)

涂装膜厚

干膜: 30-60 μ m/道 湿膜: 65-130 μ m/道(白色)

Spreading rate

 Theoretical: 0.109kg/ m²/40 microns (white)

涂覆率

理论值 : 0.109 千克/平方米/40 μ m (白色)

Practical: Various depending on surface conditions, environment, applications, etc.

实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。

STORAGE

储存

Shelf temperature

-10°C-40°C

储存温度

Shelf life

1 year

储存期限

1 年

Flash point

Greater than 8°C

闪点

8°C 以上

APPLICATION DATA

施工数据

Pot life

混合使用期

Temperature (°C) 温度	5	10	20	30
Pot life (hrs) 混合使用期	8	6	5	3

Application methods

施工方法

Airless spray, air spray, brush and roller
无气喷涂、空气喷涂、刷涂及辊涂

Airless spray	无空气喷涂	Recommended 推荐
Nozzle tip	喷嘴尺寸	0.021-0.023
Fluid pressure	出口压力	100-150kg/cm ²
Thinning	稀释比率	0-3% by volume (体积比)

Thinner

稀释剂

Retan Thinner

聚氨酯稀释剂

Application temperature

施工温度

-10°C -40°C

Drying time &
Overcoating interval

干燥时间&涂装间隔

Temperature (°C)	温度	-5	5	10	20	30
Dry to touch (hrs)	指触干燥	4	2	1.5	1	1
Dry hard (hrs)	半硬干燥	24	16	12	10	6
Min. interval (hrs)	最小涂装间隔	30	24	20	16	12
Max. interval (days)	最大涂装间隔	-	-	-	-	-

PAINTING SYSTEM
涂装配套
Preceding coat

适用下涂

Epomarine EX 500, Super EX 21 AC, Retan Undercoat, or according to the coating systems of Kansai.

Epomarine EX 500, Super EX 21 AC, Retan Undercoat, 或参考我司推荐配套。

SURFACE PREPARATION
表面处理

The primer surface should be clean, dry and free of all contamination.

底漆表面应清洁干燥，无污物。

Observe the overcoating intervals specified for the primer.

注意施工时与底漆的涂装间隔。

SAFETY PRECAUTIONS
安全措施

A health and safety data sheet for product is available upon request.

Minimum precautions to be taken in dealing with all paints are:

任何油漆施工中均应保证提供以下措施:

- Avoid skin and eye contact.
避免接触皮肤和眼睛。
- If paint comes into contact with the skin, wash with warm water and/or a suitable cleanser. If paint comes into contact with the eyes, flush with copious amount of water and seek immediate medical

attention.

如果油漆接触到皮肤，应用温水以及（或者）适当的清洗剂清洗。如果油漆接触到眼睛，应用大量水冲洗并立即就医。

- Ensure good ventilation.
保证良好的通风。
- Paint products contain flammable materials. Please keep them away from sparks and prohibit any smoking in the vicinity.
涂料中含有可燃物质。请远离火花并禁止在临近地区吸烟。
- Observe all health and safety data on the container.
现场遵守一切健康安全规定。

DISCLAIMER

提请注意

The information given on this sheet is to the best of our knowledge and accurate at the time of printing. Since conditions of use are beyond the manufacture's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展,此中所有信息均以我方确认为主。
